This MotoCAP safety rating applies to:

Brand	Dainese
Model	Prima72
Type	Jacket - Leather
Date purchased	8 February 2021
Sizes tested	54 and 56
Test garment gender	Male
Style	All Purpose
RRP	$799.95

Test Results Summary	Rating	Score
MotoCAP Protection Rating	★★★	52.3
Abrasion	7/10	5.50
Burst	10/10	1434
Impact	5/10	35.0
MotoCAP Breathability Rating	★	0.125
Moisture Vapour Resistance	-	130.8
Thermal Resistance	-	0.272
Water resistance	N/A	N/A

This garment is fitted with impact protectors for the elbows and shoulders. A pocket is provided for an aftermarket back protector. There are no vents to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.



Removable liners

Thermal liner	☐
Water-resistant liner	☐

Removable impact protection

	Pockets	Armour
Elbow	✓	✓
Shoulder	✓	✓
Back	✓	☐

Zone 1	Zone 2	Zone 3	Zone 4
High risk of abrasion High risk of impact	High risk of abrasion	Medium risk of abrasion	Low risk of abrasion

Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.

Abrasion Resistance Performance	
Abrasion rating	7/10
Abrasion score	5.50

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zones 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Zones 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material A	40%	10.00	10.00	10.00				10.00	G
Material B	60%	5.03	3.25	3.38	4.75	4.08	4.00	4.08	A
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	**Average**	
Material B	100%	5.03	3.25	3.38	4.75	4.08	4.00	4.08	G
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	**Average**	
Material B	100%	5.03	3.25	3.38	4.75	4.08	4.00	4.08	G

Details of materials used in jacket

Material A	Leather patch over leather shell with fabric inner liner
Material B	Leather shell with fabric inner liner

Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.

Burst Strength Performance	
Burst rating	10/10
Burst score	1434

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	1954	1858	745	1200	889	1502	1358	G
Zones 3 & 4	1850	1148	1962	1958	1695	1803	1736	G

Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximium force for each impact zone. Areas shaded black are not considered for impact protection ratings.

Impact Protection Performance	
Impact rating	5/10
Impact score	35.0

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Impact Protector Results: - The table below shows the average and maximum force transmitted through each impact protector type in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Elbow		Shoulder	
Average force (kN)	19.3	A	19.3	A
Maximum force (kN)	20.9	A	22.4	A
Coverage of Zone 1 area	90%		90%	
Coverage of Zone after displacement	70%		90%	

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow			Shoulder		
Strike location	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	19.8	20.9	20.5	17.7	16.8	20.9
Impact Protector 2	19.8	17.6	19.7	19.2	19.3	20.2
Impact Protector 3	20.0	18.0	17.9	19.7	17.8	22.4

Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable liners		With water-resistant liner	
Breathability rating	✈	Breathability rating	N/A
Breathability score	0.125	Breathability score	N/A

Moisture Vapour Resistance - R_{et} (kPa.m^2/W)	1	2	Average
Without removable liners	127.5	134.0	130.8
With water-resistant liner	N/A	N/A	N/A

Thermal Resistance - R_{ct} (K.m^2/W)	1	2	Average
Without removable liners	0.269	0.274	0.272
With water-resistant liner	N/A	N/A	N/A

Water spray and rain resistance

This jacket has not been advertised as water-resistant so has not been tested for water spray and rain resistance.

Assessment Details.

Brand	Dainese
Model	Prima72
Type	Jacket - Leather
Date purchased	8 February 2021
Tested by	AMCAF, Deakin University
Garment test reference	J20L03
Rating first published	April 2021
Rating updated	13 April 2021