



This MotoCAP safety rating applies to:

Brand: Revit
Model: Eclipse

Type: Jacket - Textile

Date purchased: 16 November 2019

Sizes tested: L and XL Gender: M

Style: All Purpose Test code: J19T32


Test Results Summary:

	Rating	Score
MotoCAP Protection Rating	*	25.4
Abrasion	1/10	0.45
Burst	8/10	874
Impact	7/10	48.1
MotoCAP Comfort Rating	***	0.602
Moisture Vapour Resistance		16.3
Thermal Resistance		0.163
Water resistance	N/A	N/A

This garment is fitted with impact protectors for the elbows, shoulders and back. Mesh panels are located in the arms, chest and back to allow airflow movement through the garment.

Jacket and Pants - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.





Abrasion Resistance

The garment was tested for abrasion resistance in accordance with MotoCAP test protocols. The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone.

Details of materials used in garment:

Material A: Woven fabric shell with mesh inner liner

Material B: Mesh shell with mesh inner liner

Zone	Coverage	Abrasion time for each test (seconds)						Average
	(%)	1	2	3	4	5	6	(seconds)
Zone 1 and 2	areas (High abra	asion risk)						
Material A	100%	0.68	0.35	0.03	0.77	0.60	0.76	0.53 P
Zone 3 area (Medium abrasio	n risk)						
Material A	30%	0.68	0.35	0.03	0.77	0.60	0.76	0.53 P
Material B	70%	0.32	0.26	0.28	0.22	0.24	0.17	0.25 P
Zone 4 area (Low abrasion ris	sk)						_
Material A	20%	0.68	0.35	0.03	0.77	0.60	0.76	0.53 M
Material B	80%	0.32	0.26	0.28	0.22	0.24	0.17	0.25 P

Abrasion times are capped at a maximum of 10.00s.

The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table above. The colour coding is based on the worst performing material in each zone.



		Good	Acceptable	Marginal	Poor
Determining Criteria					
High abrasion risk	Zone 1/2:	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3:	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4:	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4




Burst Strength

The garment's burst strength was tested in accordance with MotoCAP test protocols. The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure (kPA)

Area	1	2	3	4	5	Average
Zones 1 & 2	935	650	662	870	695	763 M
Zone EZ	1011	551	1416	818	759	911 A
Zones 3 & 4	532	1207	1330	872	1177	1024 G

The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table above.





Impact Protection


The garment was tested for impact protection and coverage in accordance with MotoCAP test protocols. The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone.

Impact protector type	Elbow	Shoulder
Average force (kN)	22.9 A	21.4 A
Maximum force (kN)	30.2 P	27.1 M
Coverage of zone 1 area	180%	130%
Coverage of zone after displacement	80%	100%

Individual test results

Impact force (kN)	Elbow	Shoulder				
Strike location	Α	В	С	Α	В	С
Impact Protector 1	25.4	25.0	30.2	17.4	19.7	27.1
Impact Protector 2	17.5	20.7	23.1	19.2	19.8	25.7
Impact Protector 3	18.5	20.2	26.1	18.1	19.3	26.0

The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table above. The colour coding is based on the worst performing score for average or maximium force for each impact zone.



^{*} Poor may also indicate that no impact protector, or impact protector pocket is present in the garment Areas shaded black are not considered in the impact protection ratings.



Thermal comfort

The garment was tested for thermal comfort following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

	1	2	Average
Moisture Vapour Resistance - Ret	15.5	17.0	16.3
(kPam²/W)			
	1	2	Average
Thermal Resistance - R _{ct}	0.167	0.159	0.163
(Km²/W)			

Water spray and rain resistance

This garment has not been advertised as water resistant so has not been tested for water spray and rain resistance.