



This MotoCAP safety rating applies to:

Brand: Neo Model: Prime

Type: Glove - Leather

Date purchased: 12 September 2022

Sizes tested: S, M and 3XL

Test glove gender: Male
Style: All Purpose
RRP: \$105.00

Test Results Summary:

| | Rating | Score |
|---------------------------|--------|-------|
| MotoCAP Protection Rating | * | 1.3 |
| Abrasion | 2/10 | 1.23 |
| Seam strength | 1/10 | 1.2 |
| Impact | 3/10 | 6.5 |
| Water resistance | 10/10 | 0.4 |

This glove is fitted with impact protectors for the knuckles area only. There is no provision for ventilation to allow airflow movement through the glove.

Gloves - Crash Impact Risk Zones

This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1
High risk of impact
High risk of abrasion

Zone 2
High risk of abrasion

Zone 3

Medium risk of abrasion



Abrasion Resistance

The gloves were tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each Zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

| Abrasion rating | 2/10 |
|-----------------|------|
| Abrasion score | 1.23 |

| Determining Criteria | Area | Good | Acceptable | Marginal | Poor |
|-----------------------------|------------|-------|------------|-----------|-------|
| High abrasion risk | Zone 1 & 2 | > 4.0 | 2.7 - 4.0 | 1.2 - 2.6 | < 1.2 |
| Medium abrasion risk | Zone 3 | 2.5 | 1.8 - 2.5 | 0.8 - 1.7 | < 0.8 |

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

| Zones 1 | Coverage (%) | Sample 1 | Sample 2 | Sample 3 | Sample 4 | Sample 5 | Sample 6 | Average | |
|------------|--------------|----------|----------|----------|----------|----------|----------|---------|---|
| Material A | 40% | 10.00 | 10.00 | 10.00 | 10.00 | 10.00 | 10.00 | 10.00 | G |
| Material B | 60% | 0.75 | 0.95 | 0.65 | 0.59 | 0.63 | 1.39 | 0.83 | Р |
| Zone 2 | Coverage (%) | Sample 1 | Sample 2 | Sample 3 | Sample 4 | Sample 5 | Sample 6 | Average | |
| Material C | 35% | 1.30 | 5.00 | 0.72 | 2.22 | 3.83 | 1.22 | 2.38 | M |
| Material B | 65% | 0.75 | 0.95 | 0.65 | 0.59 | 0.63 | 1.39 | 0.83 | Р |
| Zone 3 | Coverage (%) | Sample 1 | Sample 2 | Sample 3 | Sample 4 | Sample 5 | Sample 6 | Average | |
| Material C | 80% | 1.30 | 5.00 | 0.72 | 2.22 | 3.83 | 1.22 | 2.38 | Α |
| Material D | 20% | 0.96 | 1.50 | 1.99 | 0.80 | 1.11 | 1.09 | 1.24 | М |

Details of materials used in glove - derived from manufacturer provided information

| Material A | Hard-shell armour over foam layer, water-resistant layer and fleece inner liner |
|------------|--|
| Material B | Suede leather shell, water-resistant layer and fleece inner liner |
| Material C | Woven fabric shell, water-resistant layer and fleece inner liner |
| Material D | Suede patch over suede leather shell, water-resistant layer and fleece inner liner |



Seam Tensile Strength

The tensile strength of the gloves seams and glove restraint (the force required to drag off a properly fastened glove) were tested in accordance with MotoCAP test protocols. The diagram below illustrates the tensile strength and wrist restraint results in terms of the likely performance of the glove in a crash and is a pictorial representation of the data from the tables below.



| Seam Strength Performance | | | | |
|---------------------------|------|--|--|--|
| Seam strength rating | 1/10 | | | |
| Seam strength score | 1.2 | | | |

| Determining Criteria | Unit | Good | Acceptable | Marginal | Poor |
|-----------------------------|--------|-------|------------|----------|------|
| Seam tensile strength | (N/mm) | > 11 | 9 - 11 | 6 - 8.9 | < 6 |
| Glove restraint | (N) | > 200 | 100 - 200 | 50 - 99 | <50 |

Individual Seam Strength Results: - The table below shows the seam tensile strength in newtons per millimeter (N/mm) for each seam tested by Zone and the average result for each Zone.

Seam tensile strength (N/mm)

| Area | 1 | 2 | 3 | 4 | 5 | Average |
|-------------|------|------|------|------|------|---------|
| Zones 1 & 2 | 4.68 | 5.49 | 5.72 | 5.27 | 4.64 | 5.16 P |
| Zone 3 | 6.46 | 4.38 | 8.58 | 9.50 | 4.37 | 6.66 M |

Individual Glove Restraint Results: - The table below shows the force required to remove the restrained glove in newtons (N) for each of the five gloves tested and the average result.

Glove restraint (N)

| Glove | 1 | 2 | 3 | 4 | 5 | Average |
|-----------------|------|------|------|------|------|---------|
| Wrist restraint | 36.9 | 37.3 | 44.3 | 43.2 | 38.9 | 40.1 P |



Impact Protection

The glove was tested for impact protection and coverage In accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered in the impact protection ratings.



Impact Protection Performance

| Impact rating | 3/10 |
|---------------|------|
| Impact score | 6.5 |

| Determining Criteria | Unit | Good | Acceptable | Marginal | Poor |
|-----------------------------|------|------|------------|----------|------|
| Impact force | (kN) | < 2 | 2 - 4.9 | 5 - 8 | > 8 |

^{*} Poor may also indicate that no impact protector is present in the glove

Impact Protector Results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage in percentage (%) within the Zone. Impact forces are capped at a maximum of 10.0kN.

| Impact protector type | Knuckles | Palm |
|-------------------------|----------|------|
| Average force (kN) | 2.3 A | Р |
| Maximum force (kN) | 2.7 A | Р |
| Coverage of zone 1 area | 100% | 0% |

Individual test results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and the position of the strike. Impact forces are capped at a maximum of 10.0kN.

| Impact protector type | Knuckles | | | Palm | No impact protector present |
|-----------------------|----------|-----|-----|------|-----------------------------|
| Strike number | 1 | 2 | 3 | 1 | 2 |
| Impact Protector 1 | 2.0 | 2.1 | 2.2 | | |
| Impact Protector 2 | 2.7 | 2.2 | 2.3 | | |
| Impact Protector 3 | 2.5 | 2.5 | 2.1 | | |



Water spray and rain resistance

This glove is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the glove and under-glove due to water absorption.

| | Water absorbe | ed by glove | Water absorbed by cotton glove | | |
|---------|---------------|----------------|--------------------------------|----------------|--|
| | Volume (ml) | Percentage (%) | Volume (ml) | Percentage (%) | |
| Pair 1 | 1.3 | 0.6% | 1.3 | 6.7% | |
| Pair 2 | 0.2 | 0.1% | 0.2 | 1.0% | |
| Average | 0.8 | 0.3% | 8.0 | 3.8% | |

Location of wetting:

There was no visible wetting to the cotton under-glove in all four of the gloves tested.

Assessment Details.

Brand Neo Model Prime

Type Glove - Leather
Date purchased 12 September 2022
Tested by AMCAF, Deakin University
Report approved by MotoCAP Chief Scientist

Garment test reference G21L36
Rating first published April 2023
Rating updated 4 April 2023