


This MotoCAP safety rating applies to:


Brand	Triumph
Model	Braddan Mesh
Type	Jacket - Textile
Date purchased	20 August 2024
Sizes tested	L and XL
Test garment gender	Male
Style	All Purpose
RRP	\$545.37


Test Results Summary	Rating	Score
MotoCAP Protection Rating	★★	37.6
Abrasion	2/10	1.84
Burst	10/10	1349
Impact	7/10	49.8
MotoCAP Breathability Rating	★★★★	0.431
Moisture Vapour Resistance	-	30.2
Thermal Resistance	-	0.217
Water resistance	1/10	86.4


This garment is fitted with impact protectors for the elbows, shoulders and back. Mesh panels are located in the chest and back to allow airflow movement through the garment. There are zipped vents in the sides of the back to allow controlled airflow movement through the garment. The breathability rating is based on tests of the garment's materials when all vents are closed. The breathability of this product may be better when the vents are opened. This garment has a removable water-resistant liner. The breathability rating above was achieved with the water-resistant liner removed. When tested with the water-resistant liner installed, the breathability rating reduced to half a star.


Jacket and Pants - Crash Impact Risk Zones


This diagram is a pictorial representation of the crash impact risk Zones.



Zone 1

 High risk of abrasion
 High risk of impact

Zone 2

 High risk of abrasion

Zone 3

 Medium risk of abrasion

Zone 4

 Low risk of abrasion

Removable liners

Thermal liner	<input type="checkbox"/>
Water resistant liner	<input checked="" type="checkbox"/>

Removable impact protection

	Pockets	Armour
Elbow	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Shoulder	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Back	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Chest	<input type="checkbox"/>	<input type="checkbox"/>

Abrasion Resistance

The jacket was tested for abrasion resistance in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely abrasion performance of the materials in each zone calculated from the data in the table below. The colour coding is based on the worst performing material in each zone.



Abrasion Resistance Performance

Abrasion rating	2/10
Abrasion score	1.84

Determining Criteria	Area	Good	Acceptable	Marginal	Poor
High abrasion risk	Zone 1 & 2	> 5.6	3.0 - 5.6	1.3 - 2.9	< 1.3
Medium abrasion risk	Zone 3	> 2.5	1.8 - 2.5	0.8 - 1.7	< 0.8
Low abrasion risk	Zone 4	>1.5	1.0 - 1.5	0.4 - 0.9	< 0.4

Individual Abrasion Resistance Results: - The table below shows the test results for time to abrade through all layers of the materials. Calculated for each sample by Zone, type and area coverage of each material as a proportion of that Zone. Abrasion times are capped at a maximum of 10.00s.

Abrasion time for each test (seconds)

Zone 1 & 2	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material A	60%	8.37	10.00	5.96	10.00	9.11	10.00	8.91	G
Material B	40%	1.29	1.14	1.17	3.28			1.72	M
Zone 3	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material C	100%	0.68	0.61	0.59	0.47	0.41	0.62	0.56	P
Zone 4	Coverage (%)	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Material C	5%	0.68	0.61	0.59	0.47	0.41	0.62	0.56	M
Material D	95%	0.34	0.17	0.13	0.34	0.36	0.31	0.28	P

Details of materials used in jacket

Material A	Quilted leather shell with mesh inner liner
Material B	Quilted fabric shell with mesh inner liner
Material C	Fabric shell with mesh inner liner
Material D	Mesh fabric shell with mesh inner liner

Burst Strength

The jacket was tested for burst strength in accordance with MotoCAP test protocols. The diagram below illustrates the burst strength results in terms of the likely performance of the garment in an impact and is a pictorial representation of the data from the table below.



Burst Strength Performance

Burst rating	10/10
Burst score	1349

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor
Burst strength	(kPa)	> 1000	800 - 1000	500 - 799	< 500

Individual Burst Strength Results: - The table below shows the burst pressure in kilopascals (kPA) for each sample tested by Zone and the average result for each zone.

Burst pressure for each seam (kPA)

Area	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6	Average	
Zones 1 & 2	2002	1370	1320	961	1012	1695	1393	G
Zones 3 & 4	1579	1123	1359	589	1220	1154	1171	G

Impact Protection

The jacket was tested for impact protection and coverage in accordance with MotoCAP test protocols. The diagram below is a visual indication of the likely performance of each impact protector calculated from the data in the table below. The colour coding is based on the worst performing score for average or maximum force for each impact zone. Areas shaded black are not considered for impact protection ratings.



Impact Protection Performance

Impact rating	7/10
Impact score	49.8

Determining Criteria	Unit	Good	Acceptable	Marginal	Poor*
Impact force	(kN)	< 15	15 - 24	25 - 30	> 30

* Poor may also indicate that no impact protector, or impact protector pocket is present in the garment

Individual Impact Protector Results: - The table below shows the test results for each strike on each impact protector in kilonewtons (kN) and their area of coverage as a proportion (%) of the Zone. Individual strike results are capped at a maximum of 50kN.

Impact protector type	Elbow		Shoulder	
Average force (kN)	16.9	A	17.2	A
Maximum force (kN)	19.8	A	20.4	A
Coverage of Zone 1 area	110%		105%	
Coverage of Zone after displacement	90%		100%	

Individual Impact Protector Results: - The table below shows the test results for each strike on individual impact protectors in kilonewtons (kN) and the position of the strike. Individual strike results are capped at a maximum of 50kN.

Force transfer for each impact strike (kN)

Impact protector type	Elbow			Shoulder		
	Centre	Mid	Edge	Centre	Mid	Edge
Impact Protector 1	15.2	17.8	17.5	15.5	17.1	19.5
Impact Protector 2	15.4	17.3	18.8	14.9	17.2	18.8
Impact Protector 3	15.4	15.2	19.8	15.7	15.4	20.4

Breathability

The jacket was tested for breathability following the MotoCAP test protocols. The table below shows the moisture vapour resistance and the thermal resistance values obtained.

Without removable liners		With water-resistant liner	
Breathability rating	★★★	Breathability rating	★
Breathability score	0.431	Breathability score	0.152

Moisture Vapour Resistance - R_{et} (kPa.m ² /W)	1	2	Average
Without removable liners	30.6	29.8	30.2
With water-resistant liner	106.8	103.3	105.1
Thermal Resistance - R_{ct} (K.m ² /W)	1	2	Average
Without removable liners	0.219	0.215	0.217
With water-resistant liner	0.249	0.283	0.266

Water spray and rain resistance

This jacket is advertised as water-resistant, and so has been tested for water spray and rain resistance according to the MotoCAP test protocols. The table below shows the water absorbed (ml) and the wetting proportion (%) of the garment and undergarments due to water absorption.

	Water absorbed by garment		Water absorbed by underwear		Water Resistance Performance	
	Volume (ml)	Percentage (%)	Volume (ml)	Percentage (%)		
Jacket 1	757	49%	197	70%	Water rating 1/10 Water Score 86.39	
Jacket 2	677	41%	303	103%		
Average	717	45%	250	86%		

Location of wetting

There was major wetting to the cotton underwear present at the abdomen, neck and chest for one jacket and at the cuffs of the sleeves and chest of the other jacket tested.

Assessment Details.

Brand	Triumph
Model	Braddan Mesh
Type	Jacket - Textile
Date purchased	20 August 2024
Tested by	AMCAF, Deakin University
Report approved by	MotoCAP Chief Scientist
Garment test reference	J24T44
Rating first published	November 2024
Rating updated	19 November 2024